

Examine's Copy

AN 1980:46029 HCAPLUS
DN 92:46029
TI Thermoplastic treatment of a zinc-aluminum-copper alloy
IN Marczak, Ryszard; Ciach, Ryszard; Kwaskiewicz, Franciszek; Szumniak, Jerzy; Piekarski, Zygmunt
PA Wojskowy Instytut Techniki Panczernej i Samochodowej, Pol.
SO Pol., 2 pp.
CODEN: POXXA7
DT Patent
LA Polish
FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	PL 102236	P	19790331	PL 1975-184252	19751023
AB	The thermomech. treatment of the bearing Zn alloys contg. Al 10-75, Cu 0-5, and Fe, Si, Be, Ti, Cr, Ni, Mg, Mn, and Li <3% increases the dimensional stability and retains high abrasive wear resistance. The castings are homogenized at 320-400.degree. 1-14 h, air quenched to the isothermal transformation at 200-270.degree., and held 0.5-30 h, hot rolled or extruded at 85-400.degree., annealed at 320-400.degree. 1-12 h, air quenched to 200-270.degree., held 0.5-30 h, hot roled or extruded at 85-400.degree., annealed at 320-400.degree. 1-12 h, air or water quenched to 80-280.degree., held 1-24 h, and aged at 70-160.degree. 2-96 h. If the forming is carried out in several stages, then the interstage annealing at 180-400.degree. 0.25-10 h and quenching are introduced. The improved properties of the alloy ater the thermoplastic treatment are due to a high dispersion of Al and Zn phases attained during the treatment.				

2-5